

RESEARCH MEMORANDUM

MEASUREMENT OF DISTORTION IN SECOND EXPERIMENTAL CONTROL

ROD WITH TEMPERATURE PATTERNS SIMULATING SHIM ROD OUT

AND SHIM ROD 50 PERCENT INSERTED FOR ARGONNE

FOR REFERENCE

NAVAL REACTOR

By A. F. Lietzke and T. F. Nagey

Lewis Flight Propulsion Laboratory Cleveland, Ohio LIBRARY COPY

JAN 21 196U

LANGLEY FIELD, VIRGINIA

NATIONAL ADVISORY COMMITTEE FOR AERONAUTICS

WASHINGTON

September 26, 1951 Declassified December 10, 1959 NACA RM E51E25

NATIONAL ADVISORY COMMITTEE FOR AERONAUTICS

RESEARCH MEMORANDUM

MEASUREMENT OF DISTORTION IN SECOND EXPERIMENTAL CONTROL ROD

WITH TEMPERATURE PATTERNS SIMULATING SHIM ROD OUT

AND SHIM ROD 50 PERCENT INSERTED FOR ARGONNE

NAVAL REACTOR

By A. F. Lietzke and T. F. Nagey

SUMMARY

Thermal distortion tests were made on a stainless-steel clad, cadmium-silver control rod furnished by the Argonne National Laboratory. Two temperature patterns supplied by the Argonne National Laboratory were simulated in these tests; one represented the shim-rod-out condition and the other the shim-rod-50-percent-inserted condition.

The greatest reduction in clearance affected by thermal distortion was 0.076 inch. No permanent set of the control rod was observed after repeated heating and cooling cycles.

INTRODUCTION

Thermal distortion tests were made at the NACA Lewis laboratory on a stainless-steel clad, cadmium-silver core xenon control rod furnished by the Argonne National Laboratory. Distortion measurements on the first experimental control rod with temperatures intended to simulate 50-percent shim-rod insertion are presented in reference 1. Thermal-distortion measurements on a later model xenon rod with temperature patterns simulating operation with shim rods 50 percent inserted and with shim rods out are presented herein. The temperature patterns used as a basis for the tests were obtained from the Argonne laboratory.

EQUIPMENT

Control rod. - The control rod core was made of an alloy of 75-percent silver and 25 percent cadmium and was clad with stainless steel. A cross section of the rod was in the shape of a cross having a span of 4 inches. The core alloy thickness was 1/8 inch with a cladding thickness

2207

66-1

202

of 3/64 inch, resulting in a total arm thickness of 7/32 inch. The rod had an over-all length of 53.75 inches. The cladding joints for the tips of the arms and ends of the rod were welded. After fabricating, the rod was hot-rolled in order to form a bond between the core alloy and the stainless steel. The rod was stress relieved.

Several weld failures were found on the rod as received from the Argonne laboratory. Figure 1 shows the most severe failure found. The failures occurred at the welded juncture of the cladding at the tip of the cross at several locations along the length of the rod.

Method of supporting control rod. - The rod was supported essentially as in reference 1. The vise which holds the control rod, however, was bolted indirectly to the mounting plate through insulating material to reduce the heat flow to the mounting plate. Strain gages were located near the fixed end of the rod to insure freedom from stress during the clamping of the rod in the mounting vise.

Method of obtaining temperature distribution. - The control rod was heated by a 75 KVA induction heater. Axial temperature distributions were obtained by varying the axial spacing of the heater coil turns. Transverse temperature gradients were obtained by making the heating coil and the rod nonconcentric and by a series of air jets mounted along the rod and directed toward the center of the cross. The air jets were provided by 0.0135-inch diameter holes located 3/8 inch apart, and were controllable in groups of 14 by a valve.

Temperature patterns were measured by means of 104 thermocouples distributed between 8 stations located along the axis of the rod as indicated in tables I(a) and II(a) and (b). In addition, thermocouples were located at stations $20\frac{1}{2}$, 21, $21\frac{1}{2}$, $22\frac{1}{2}$, 23, and $23\frac{1}{2}$ inches from the free end of the rod (these positions are adjacent to specific coils of the induction heater) to note any local hot spots due to the proximity of the induction coils. No hot spots at these locations were indicated and the temperatures at these special locations are not reported.

Tables I(a) and II(a) and (b) list the required temperatures at each station as requested by the Argonne laboratory and the measured temperatures in the several runs.

Method of measuring distortion. - Distortion on the rod was measured as in reference 1 by means of dial indicators. Normally two indicators were located at each tip of the cross in positions along the length of rod as given in tables I(b) and II(c) and (d). The indicators were mounted on four vertical supports fastened to the same mounting plate as the control rod (see fig. 2). These supports were protected from conduction and radiation to eliminate thermal distortion in the supports themselves.

Dial indicators were also supplied to indicate any motion of these supports. Fused quartz rods, 12 inches in length, were used to transmit the motion of the control rod to the dial indicators. The use of fused quartz eliminated the need for a correction for thermal expansion of the indicator rods. The reproducibility of the indicator readings was within ± 0.002 inch. A vibrator was attached to the mounting plate and was operated before each set of readings was taken to reduce the effect of static friction of the gages.

RESULTS AND DISCUSSION

Summary of data. - The desired temperature patterns for the tests reported herein were obtained from the Argonne laboratory. Distortion measurements were made with two different temperature patterns; one pattern was intended to simulate operation with the shim rods inserted 50 percent, and one pattern was with the shim rods out. The location of the thermocouples and the corresponding surface temperatures are listed in tables I and II, along with the corresponding distortion measurements. For each thermocouple location, the temperatures desired by the Argonne laboratory and the temperatures experimentally obtained in the present tests are listed. The distance of the thermocouple station from the free end of the rod is represented by Z. The thermocouple locations at each value of Z are designated by numbers from 1 to 16. As indicated in the tables, 16 thermocouples were not installed at each value of Z listed.

The displacement of the tips of the cross are indicated in tables I and II by the values of Δx and Δy with their proper signs. These values are given with reference to the unheated position of the control rod. The distortion measurements are those corresponding to the temperatures obtained in the tests, which differed slightly from the temperatures desired by the Argonne laboratory.

Distortion of control rod. - The motion of tips 1 and 9 in the y-direction and of tips 5 and 13 in the x-direction are plotted in figures 3 and 4. It would be expected that the sign of the y displacement would always be the same (negative in this case) at the free end, inasmuch as the desired temperatures at location 1 are equal to or higher than those at location 9 in both desired temperature patterns. Figure 3, however, shows Δy to be positive at the free end. Examination of the temperature patterns obtained in table I(a) indicates that near the fixed end of the control rod the temperatures obtained at location 1 were lower than those at location 9 which accounts for the change in direction of displacement. Figure 4 shows Δy to be negative at the free end and inspection of the data in table II(a) indicate that the test temperatures and the desired temperatures agree more closely than in table I. Figure 4(c) and (d) represent the distortion for a slightly different

temperature pattern than those in figures 4(a) and (b), the difference being that the fixed end temperatures more nearly matched the required values. The distortions as measured in either case are, however, nearly the same.

The maximum reduction in clearance cannot be determined from figures 3 and 4 alone, inasmuch as the motion of each point in one direction only is shown and hence reference must be made to the tables. It can be seen from the distortion data given in tables I and II that the values for reduction in clearance given in figures 3 and 4, are within 0.002 inch from the maximum. The greatest reduction in clearance obtained in the tests was 0.076 inch as indicated by the data in the tables.

SUMMARY OF RESULTS

The results of tests on a stainless-steel clad, silver-cadmium control rod under the influence of two temperature patterns which simulated the shim-rod-out condition and the shim-rod-50-percent-inserted condition can be summarized as follows:

- 1. The greatest reduction in clearance obtained in the tests was 0.076 inch.
- 2. No permanent set of the control rod was observed after repeated heating and cooling cycles.

Lewis Flight Propulsion Laboratory,
National Advisory Committee for Aeronautics,
Cleveland, Ohio,

REFERENCES


1. Nagey, T. F., and Lietzke, A. F.: Measurement of Distortion in First Experimental Control Rod for Argonne Naval Reactor.

NACA RM E51A30, 1951.

2207

TABLE I - SIMULATED SHIM RODS INSERTED 50 PERCENT.


(a) Temperatures.



				Fixed end		7777	_					9					CA
Z (in.)	Run	<u> </u>	, ·					Therm	ocoupl	e loc	ation			_			
		1	2	3	4	5	6	7	. 8	9	10	11	12	13	14	15	16
1	(a) 1 2	476 479 476	484 481	481 481 481	463 484 479	471 480 476	463 480 476	1484 1482 1482	459 483 480	467 479 477	459 481 479	455 482 479	463 482 479	471 476 474	463 458 434	455 485 482	466 484 481
8	(a) 1 2	525 529 530	500	476	P35	513 513 515	492 509 509	476 479 481	767 767 787	502 504 504	14817	476	492	213 214 213	492 511 512	476 482 482	500 521 521
15	(a) 1 2	509 1490 1487	490 487 487	471 470 470	762 765 7687	500 497 495	484 495 495	471 478 478	478 495 495	200 201 735	<u>ተ</u> 7ዓ 491 492	471	484 478 479	500 479 480	484 479 480	471 461 459	և90 487 487
22	(a) 1 2	458 452 450	455	452	454	1456 1419 1417	15 15 15 15 15 15 15 15 15 15 15 15 15 1	452 456 447	727 727 723	455 451 451	453	452	7+27+	456 441 438	1473 1473 14214	1452 1413 1413	1455 144 1455
29	(a) 1 2	455 441 436	1443 1449 1453	451 452 451	1451 1451 1452	77-0 77-0 727-	14.9 14.9 1452	451 453 452	फूर्फ फूर्फ	153 151 153	452 453 452	451 455 453	452 447 446	454 444 436	452 445 443	451 448 437	453 441 436
36	(a) 1 2	723 723 723	451	450	451	452 458 452	451 461 457	450 468 465	450 476 471	451 473 467	450	450	451	452 459 452	7190 7197 712.J	450 467 462	451 461 459
J#3	(a) 1 2	148 1461 1456	448 470 465	կկՑ 476 471	կկ8 473 468	Ы48 467 462	448 469 465	448 476 473	448 491 475	կկ8 կ78 կ71	կկ8 կ82 կ78	448 482 478	448 471 465	ЦЦ8 Ц65 Ц60	ԱԱ8 467 462	448 476 470	7463 7466 7478
50	(a) 1 2	448 439 425	11118	դդջ	148	448 436 430	1770 727 1778	եկ8 482 473	490 490 448	ևև8 479 465	Ji-798	PF8	1:148	778 778 778	448 465 456	148 482 474	72. 765 778

^aRequested by Argonne National Laboratory.


TABLE I - SIMULATED SHIM RODS INSERTED 50 PERCENT. Concluded.



Z (in)	Run	Displace- ment (in)	1	5	9	13
2	1 2	ΔΣ ΦΣ ΦΣ	0.006 .067 .004 .065	0.005 .053 .007	.047	-0.027 .060 027 .058
10	1 2	Δx Δy Δx Δy	001 .056 002	.013 .058 .016 .047	.011 .035 .010	011 .049 008 .048
20	1 2	Δx Δy Δx Δx	003 .036 003	.011 .005 .011 .005	005 .028 003 .022	002 .031 001 .031
35	1 2	Δ¥ Δ¥ Δ×	001 .015 001 .013	.010	.003	006
52	1	Δx Δy Δx Δy	.010	-	009 - 008	005

TABLE II - SIMULATED SRIM RODS OUT


(a) Temperatures; runs 1 and 2.



				erd									_ ::			منتيته	<u> </u>
Z	Run							Therm	couple	location	079						
(in.)		1	2	3	14	5	6	7	8	9	10	11	12	13	14	15	16
1	(a) 1 2	460 459 460	455 461 463	1461 1461 1449	453 461 464	458 458 459	453 458 459	459 459	451 454 457	151 151 155	72.7 7月.8 72.7	721 720 773	453 449 450	458 437 438	453 1117 1426	449 456 457	1455 1460 1460
8	(a) 1 2	476 480 481	466	455	1462	470 475 475	462 476 475	455 456 455	165 165	466 467 467	459	455	1:62	470 464 462	462 471 470	455 459 468	166 160 181
15	(a) 1 2	490 493 495	476 493 495	461 460 465	470 479 480	182 185 186	470 485 487	461 446 449	466 474 477	476 483 486	466 478 482	461 487	470 482 484	1483 1483 1485	470 482 486	799 795 795	476 488 489
22	(a) 1 2	490 500 503	476	161	471	482 487 490	471 487 490	1461 1419 1451	467 470 473	476 473 475	467	1461	1,71	780 780 785	1471 1480 1483	461 469 473	476 435 445
29	(a) 1 2	481 483 485	471 485 485	459 477 479	466 477 479	475 473 476	466 473 475	459 465 457	463 474 475	471 474 475	463 474 475	459 469 470	466 479 480	475 479 480	466 480 481	459 477 480	471 484 485
36	(a) 1 2	467 464 465	461	454	459	1462 1463	459 464 463	1454 1454	457 459 469	461 469 469	457	454	459	1199 1199 1191	458 466 465	799 799 727	762 767 793
143	(a) 1 2	种2 种3 种8	7779 7777 7778	1711.2 1711.2 1711.8	种8 种2 种8	1418 1418 1417	եկ։ ԱԿ5 ԱԿ7	148 145 148	1412 1472 148	746 744 738	1479 144 148	1478 1479 1479	7179 7173 7748	科科 科 科 科 科 科 科 科 科 科 科 科 科	한 한 한 한 8	かけQ かけ2 さが8	5年 2年 348
50	(a) 1 2	1773 1773 1779	14148	1418	148	448 441 453	1419 1419 1419	148 456 469	726 776 778	1436 1436 1445	11148	lili\$	778	148 1436 1415	448 447 458	1,48 1,62 1,72	իկ8 465 478


⁸Requested by Argonne Mational Laboratory.

TABLE II - SIMILATED SHIN RODS CUT. Continued (b) Temperatures; run 3.




Z	Run							Thermo	couple	location	n	<u> </u>	-	 . : .			
(in.)		1	2	3	L L	5	6	7	B	9	10	11	12	13	14	15	16
ı	(a) 3	1460 1449	455 452	1449 1450	1453 1449	1458 1449	453 451	1449 1452	1451 1419	1722 1722	կ51 կկ2	以() 445	453 high	458 432	453 453	իկ6 իկ6	455 453
8	(a) 3	476 475	466	455	462	1470 1465	462 466	455 447	459 456	466 457	150	455	L62	472	462 458	455 465	1.66 1.75
15	(a) 3	ዚ90 կ87	476 487	461 460	470 472	482 478	479 478	461 441	466 467	կ76 և7կ	465 472	461	472 472	1,82 1,72	1170 1171	461 461	476 473
22	(a) 3	490 491	476	461	471	482 490	1471 1492	461 450	467 474	476 478	L67	451	471	482 480	471 480	461 472	476 444
29	(a) 3	481 489	471 490	459 482	466 481	475 479	466 479	459 469	463 479	171 179	463 475	459 475	466 495	475 485	և66 և46	459 485	171 190
36	(a) 3	467 462	461	1454	459	1461 1461	459 462	454 465	457 467	461 470	457	454	459	1.61. 1.67	458 465	45h 465	461 461
43	(a) 3	1443 1443	种0 种8	1413 1414 1414	7477 7478	1115 1118	7175 7178	կկ8 կկ1	8بليا 2بليا	7775 7778	1448 1448	րիր Իրջ	կեր կկ1	7770 7772	448 437	141 141	Pris Pris
50	(a) 3	1448 1450	抽名	կկ8	8,44	448 456	1449 1449	նկ։ կ.69	ЦЦ. 1458	1418 1417	հնե	神化	PPR	7778 7774	44# 459	141A 1475	PP0

^aRequested by Argonne National Laboratory.



			Gage location							
Z (in.)	Run	Displace- ment (in.)	1	5	9	13				
2	1 2	Δж Δу Δ х Δу	0.006 039 .005 040	0.000 052 .002 053	0.006 057 .006 058	-0.017 046 016 047				
10	1 2	Дж Ду Дж Ду	.007 029 .006 030	.005 033 .006 035	.013 043 .012 045	008 029 007 030				
20	1 2	Δх Δу Δх Δу	.000 008 001 009	.005 021 .006 022	.006 027 .006 029	008 032 008 033				
35	2	Δx Δy Δx Δy	.002 003 .001 004	.009 001 .010 012	.005	007 007				
52	1 2	Δx , Δy Δx Δy	.002	.007	007 007	004				

TABLE II - SIMULATED SHIM RODS OUT. Concluded



			Gage location							
(in.)	Run	Displace- ment (in.)	1	5	9	13 .				
2	3	∆ x ∆ y	0.002 029	0.005 048	0.004 054	-0.0I4 043				
10	3	Δ y Δ y	.00 <u>4</u> 027	.007 031	.011 041	005 027				
20	3	∆ ж ∆у	002 008	.007	.013 027	006 031				
35	3	Δ х Δ у	.001 004	.013 010	.012	006				
52	3	Δ x Δy	.004	•006	007	003				




Figure 1. - Photograph of most serious weld failure.

NACA RM E51E25





Figure 2. - Photograph of setup.



(a) Variation of $\triangle x$ with Z.






Figure 3. - Distortion of control rod with temperature pattern intended to simulate shim rods inserted 50 percent; normal temperatures.




(a) Variation of Δx with Z; runs 1 and 2.




(b) Variation of Δy with Z; runs 1 and 2.

Figure 4. - Distortion of control rod with temperature pattern intended to simulate shim rods out, normal temperatures.



(c) Variation of $\triangle x$ with Z; run 3.



(d) Variation of $\triangle y$ with Z; run 3.

Figure 4. - Concluded. Distortion of control rod with temperature pattern intended to simulate shim rods out; normal temperatures.

3 1176 01435 2406

E.ess

¥